

### Manufacturer

Georgia-Pacific Gypsum LLC  
133 Peachtree Street  
Atlanta, GA 30303

Georgia-Pacific Canada LP  
2180 Meadowvale Boulevard, Suite 200  
Mississauga, ON L5N 5S3

Technical Service Hotline: 1-800-225-6119

### Description

**DensGlass® Sheathing** is a gypsum panel made of a treated, water-resistant core, surfaced with fiberglass mats and a GOLD colored primer coating. Providing superb protection from the elements, DensGlass Sheathing is resistant to delamination and deterioration due to weather exposure—even during construction delays that last as long as twelve months after installation and are backed by a limited warranty against delamination and deterioration for up to 12 months of exposure to normal weather conditions.\* DensGlass Sheathing panels are also mold-resistant, and have scored a 10, the highest level of performance for mold resistance under ASTM D3273 test method.

DensGlass Sheathing exhibits a dimensional stability that assures resistance to warping, rippling, buckling and sagging for a flat and even substrate and is noncombustible as defined and tested in accordance with ASTM E136 or CAN/ULC S114. Since DensGlass Sheathing is strong in both directions, it may be installed either parallel or perpendicular to wall framing members (always follow specific assembly installation instructions).

### Primary Uses

Because of the superior performance of DensGlass Sheathing, it is specified for exterior walls, ceilings and soffits in a wide variety of applications. These include exterior insulation and finish systems (EIFS); cavity brick or stone veneer applications; cladding such as wood siding, vinyl siding, composition siding, wood shingles, shakes, conventional stucco systems, plywood siding panels; and interior finish systems that require a substrate panel with superior fire and moisture resistance.

For EIFS applications, DensGlass Sheathing is an ideal substrate for adhesive or mechanical application of expanded polystyrene or extruded polystyrene insulation, and is recommended in all climate zones.

Manufacturers of water and air resistive barriers, which include attached flexible membranes, self-adhered membrane and liquid applied, have found DensGlass Sheathing to be a suitable substrate for their systems.

DensGlass Sheathing is an ideal product for exterior ceilings and soffits for both cold and warm climate zones. It resists sagging, even under exceptionally humid conditions. Panels are applied directly to structural framing. Surface and joints may be finished and painted, or surfaced with an exterior finish system.

### Limitations

DensGlass Sheathing is resistant to normal weather conditions, but it is not intended for immersion in water. Cascading roof/floor water should be directed away from the sheathing until appropriate drainage is installed.

Avoid any condition that will create moisture in the air and condensation on DensGlass Sheathing. The use of forced air heaters creates volumes of water vapor which, when not properly vented, can condense on building materials. The use of these heaters and any resulting damage is not the responsibility of Georgia-Pacific Gypsum. Consult heater manufacturer for proper use and ventilation.

\* For complete warranty details, visit [www.gpgypsum.com](http://www.gpgypsum.com).

When DensGlass Sheathing panels are used in slanted wall applications, that portion of the wall must be temporarily protected from the elements. Do not allow water to pond or settle on sheathing. Also, exposed wall ends must be covered to prevent water from infiltrating the cavity.

Georgia-Pacific Gypsum does not warrant and is not responsible or liable for the performance of the cladding or exterior systems applied over DensGlass Sheathing. The suitability and compatibility of any system is the responsibility of the system manufacturer or design authority.

Do not laminate masonry surfaces to DensGlass Sheathing; use furring strips or framing.

DensGlass Sheathing is not intended for roof applications. For roof applications, consult our DensDeck® Roof Board brochure.

DensGlass Sheathing is not intended for interior or exterior tile applications. For interior tile applications, consult our DensShield® Tile Backer brochure.

DensGlass Sheathing should not be used in lieu of plywood where required.

Do not apply DensGlass Sheathing below grade.

For all installations, design details such as fasteners, sealants and control joints per system specifications must be properly installed. Openings and penetrations must be properly flashed and sealed. Failure to do so will void the warranty.

Do not use DensGlass Sheathing as a base for nailing or mechanical fastening. Fasteners should be flush to the face of the board, not countersunk.

### Technical Data

DensGlass Sheathing is noncombustible as described and tested in accordance with ASTM E136 or CAN/ULC S114.

DensGlass Sheathing exceeds ASTM C1396 sheathing standards for humidified deflection by a factor of 10 in tests over the standard for regular gypsum sheathing.

5/8" (15.9 mm) DensGlass® Fireguard® Sheathing is UL and ULC classified **Type DGG**.

DensGlass Sheathing is manufactured to meet ASTM C1177.

Flame spread and smoke develop rating of 0/0 when tested in accordance with ASTM E84 or CAN/ULC S102.

### Handling and Use—CAUTION

This product contains fiberglass facings which may cause skin irritation. Dust and fibers produced during the handling and installation of the product may cause skin, eye and respiratory tract irritation. Avoid breathing dust and minimize contact with skin and eyes. Wear long sleeve shirts, long pants and eye protection. Always maintain adequate ventilation. Use a dust mask or NIOSH/MSHA approved respirator as appropriate in dusty or poorly ventilated areas.

Material Safety Data Sheet (MSDS) is available at [www.gpgypsum.com](http://www.gpgypsum.com) or call 1-404-652-5119.

### Product Data

Thicknesses: 1/2" (12.7 mm); 5/8" (15.9 mm) is Type X (ASTM C1177)

Width: 4' (1220 mm) standard, tolerance up to ± 1/8" (3.2 mm)

Lengths: 8' (2438 mm), 9' (2743 mm) or 10' (3048 mm) standard

Edges: Square

*continued* →

### Submittal Approvals

Job Name \_\_\_\_\_

Contractor \_\_\_\_\_

Date \_\_\_\_\_

**Physical Properties**

| Properties                                                                                 | 1/2" (12.7 mm)<br>DensGlass® Sheathing                            | 5/8" (15.9 mm)<br>DensGlass® Fireguard® Sheathing                 |
|--------------------------------------------------------------------------------------------|-------------------------------------------------------------------|-------------------------------------------------------------------|
| Width, nominal                                                                             | 4' (1219 mm) ± 1/8" (3 mm)                                        | 4' (1219 mm) ± 1/8" (3 mm)                                        |
| Length, standard                                                                           | 8' (2440 mm), 9' (2743 mm),<br>10' (3048 mm), ± 1/4" (6 mm)       | 8' (2440 mm), 9' (2743 mm),<br>10' (3048 mm), ± 1/4" (6 mm)       |
| Weight, nominal, lbs./sq. ft. (Kg/m <sup>2</sup> )                                         | 1.9 (9)                                                           | 2.5 (12)                                                          |
| Bending radius <sup>5</sup>                                                                | 6' (1829 mm)                                                      | 8' (2438 mm)                                                      |
| Racking strength <sup>6</sup> , lbs./ft. (dry) (N/m), Ultimate—not design value            | >540 (7878)                                                       | >654 (9544)                                                       |
| Flexural strength <sup>1,4</sup> , parallel, lbf. (N), 4' weak direction                   | ≥80 (356)                                                         | ≥100 (445)                                                        |
| Compressive strength                                                                       | min. 500 psi (3445 kPa)                                           | min. 500 psi (3445 kPa)                                           |
| Humidified deflection <sup>1,4</sup>                                                       | <2/8" (6 mm)                                                      | <1/8" (3 mm)                                                      |
| Permeance <sup>2</sup> , perms (ng/Pa•s•m <sup>2</sup> )                                   | >23 (1300)                                                        | >17 (970)                                                         |
| R Value <sup>3</sup> , ft <sup>2</sup> •°F•hr/BTU (m <sup>2</sup> •K/W)                    | .56 (0.099)                                                       | .67 (0.118)                                                       |
| Combustibility <sup>7</sup>                                                                | Noncombustible                                                    | Noncombustible                                                    |
| Linear expansion with moisture change, in/in %RH (mm/mm %RH) <sup>8</sup>                  | 6.25 x 10 <sup>-6</sup>                                           | 6.25 x 10 <sup>-6</sup>                                           |
| Surface burning characteristics per ASTM E84 or CAN/ULC S102: flame spread/smoke developed | 0/0                                                               | 0/0                                                               |
| Coefficient of thermal expansion, in/in/°F (mm/mm/°C)                                      | 8.5 x 10 <sup>-6</sup><br>(15.3 x 10 <sup>-6</sup> ) <sup>9</sup> | 8.5 x 10 <sup>-6</sup><br>(15.3 x 10 <sup>-6</sup> ) <sup>9</sup> |

<sup>1</sup> Tested in accordance with ASTM C473

<sup>2</sup> Tested in accordance with ASTM E96 (dry cup method)

<sup>3</sup> Tested in accordance with ASTM C518 (heat flow meter)

<sup>4</sup> Specified values per ASTM C1177

<sup>5</sup> Double fasteners on ends as needed

<sup>6</sup> Tested in accordance with ASTM E72

<sup>7</sup> As defined and tested in accordance with ASTM E136 or CAN/ULC S114

<sup>8</sup> As stated by Gypsum Association GA-235

<sup>9</sup> Tested in accordance with ASTM E228-85



U.S.A. – Georgia-Pacific Gypsum LLC  
 Canada – Georgia-Pacific Canada LP

**SALES INFORMATION AND ORDER PLACEMENT**

U.S.A. Midwest: **1-800-876-4746** West: **1-800-824-7503**  
 South: **1-800-327-2344** Northeast: **1-800-947-4497**

CANADA Canada Toll Free: **1-800-387-6823**  
 Quebec Toll Free: **1-800-361-0486**

**TECHNICAL INFORMATION**

U.S.A. and Canada: **1-800-225-6119**  
[www.gpgypsum.com](http://www.gpgypsum.com)

**TRADEMARKS** Unless otherwise noted, all trademarks are owned by or licensed to Georgia-Pacific Gypsum LLC.

**WARRANTIES, REMEDIES AND TERMS OF SALE** For current warranty information for this product, please go to [www.gpgypsum.com](http://www.gpgypsum.com) and select the product for warranty information. All sales of this product by Georgia-Pacific are subject to our Terms of Sale available at [www.gpgypsum.com](http://www.gpgypsum.com).

**UPDATES AND CURRENT INFORMATION** The information in this document may change without notice. Visit our website at [www.gpgypsum.com](http://www.gpgypsum.com) for updates and current information.

**CAUTION For product fire, safety and use information, go to [www.gp.com/safetyinfo](http://www.gp.com/safetyinfo) or call 1-800-225-6119.**

**FIRE SAFETY CAUTION** Passing a fire test in a controlled laboratory setting and/or certifying or labeling a product as having a one-hour, two-hour, or any other fire resistance or protection rating and, therefore, as acceptable for use in certain fire rated assemblies/systems, does not mean that either a particular assembly/system incorporating the product, or any given piece of the product itself, will necessarily provide one-hour fire resistance, two-hour fire resistance, or any other specified fire resistance or protection in an actual fire. In the event of an actual fire, you should immediately take any and all actions necessary for your safety and the safety of others without regard for any fire rating of any product or assembly/system.